ProRox[®] BL 960^{SA}

Old Equivalent Grade: RockTech B650

Product description

ProRox BL 960^{SA} is a blanket stone wool insulation. It can be used up to 650°C for process industrial.

Compliance

ProRox BL 960^{sA} Blanket comply with the requirements as set by internationally recognized standards like ASTM C553 Type I, II, III, IV, V, VI and VII.

Product properties

	Performance							Standard
Thermal Conductivity	Mean Temp (°C)	50	100	150	200	250	300	ASTM C177
	λ(W/mK)	0.041	0.049	0.057	0.066	0.074	0.083	
Nominal Density	100 kg/m³							EN 1602
Max Service Temperature	650°C							ASTM C411 / C447
Linear Shrinkage	Less than 2% (at max service temperature)							ASTM C356
Reaction to Fire	EuroClass A1 Surface burning characteristic; Flame spread = Passed, Smoke development = Passed							EN 13501-1 ASTM E84
рН	рН 7-12.5							ASTM C871
Chloride Content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							ASTM C871 ASTM C692 / C871
Moisture Absorption	Less than 1% weight							ASTM C1104/C1104M
Water Absorption	Less than 1 kg/m ²							EN 1609

Disclaimer: The information contained in this data sheet is believed to be correct at the date of publication. ROCKWOOL does not accept responsibility for the consequences of using ProRox in applications different from those described above.



ROCKWOOL Malaysia Sdn Bhd

Lot 4, Solok Waja 1 Bukit Raja Industrial Estate 41050 Klang, Selangor Malaysia T (+60) 3 3341 3444 F (+60) 3 3342 7290

ROCKWOOL Malaysia Sdn Bhd 175 A&B

Kawasan Perindustrian Air Keroh, Jalan Lingkungan Usaha, 75450 Melaka Malaysia T (+60) 6 233 2010 F (+60) 6 233 2012

ROCKWOOL (Thailand) Limited

ROCKWOOL (Thailand) Limite Hemaraj Eastern Industrial Estate (Map Ta Phut) 1 Soi G 2, Pakornsongkrohraj Road, Huaypong, Muang Rayong 21150 Thailand T (+66) 3868 5110 F (+66) 3868 4938