## ProRox® WM 970SA

Old Equivalent Grade: RockTech WM650HD

## **Product description**

ProRox WM  $970^{5A}$  is a lightly bonded heavy stone wool mat stitched on galvanised wired mesh with galvanised wire. The wired mat is especially suitable for industrial installations where high temperature up to  $750^{\circ}$ C and vibration resistance is required.

## Compliance

 $ProRox^{5}WM$  970<sup>SA</sup> Wired Mats comply with the requirements as set by internationally recognized standards like CINI 2.2.02 and ASTM C592 Type I, II and III.

## **Product properties**

	Performance							Standard
Thermal Conductivity	Mean Temp (°C)	50	100	150	200	250	300	ASTM C177
	λ(W/mK)	0.038	0.043	0.050	0.057	0.066	0.076	
Nominal Density	128 kg/m³							EN 1602
Max Service Temperature	750°C							ASTM C411 / C447
Linear Shrinkage	Less than 2% (at max service temperature)							ASTM C356
Reaction to Fire	EuroClass A1 Surface burning characteristic; Flame spread = Passed, Smoke development = Passed							EN 13501-1 ASTM E84
pH	pH 7-12.5							ASTM C871
Chloride Content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							ASTM C871 ASTM C692 / C871
Moisture Absorption	Less than 1% weight							ASTM C1104/C1104N
Water Absorption	Less than 1 kg/m²							EN 1609

Disclaimer: The information contained in this data sheet is believed to be correct at the date of publication. ROCKWOOL does not accept responsibility for the consequences of using ProRox in applications different from those described above.

