

AEROBOND™

POLYCHLOROPRENE ADHESIVE

Polychloroprene Contact Adhesive for Attaching Elastomeric Foam and Fiberglass Insulation onto Metal Sheet



Description

Aerobond is a modified Polychloroprene Contact Adhesive specially formulated for attaching elastomeric foam insulation (such as Aeroflex & Aerocel) and fiberglass insulation onto metal sheets used in air ducting system. The strong bonding strength of Aerobond can easily hold up 4 kgs./m² of insulation materials onto metal sheets at temperature of up to 93°C.

Application

1. Surfaces of material to be applied should be dry, clean and free from dust, grit, oil, grease or any other loose materials.
2. Apply Aerobond evenly onto metal surface and allow solvents content of Aerobond to evaporate (approximately within 30 minutes) before attaching insulation onto applied surface under firm pressure.

Storage and Shelf Life

Aerobond can be preserved for at least eight months in well sealed containers. Recommended storage temperature rang from +5°C to 35°C. Keep Aerobond under roof and avoid from direct sunlight.

Health and Safety

Advisable to work in well ventilated areas to avoid Inhalation of vapor from solvents. The solvents contained in Aerobond are inflammable and subjected to legislation regulating their storage and used. Keep away from fire, electrical spark and materials which may cause fire such as paper, cloth, plastic, etc. Aerobond contents are made of flammable liquid, but when it is completely dried the dried material is self-extinguishing material (Class UL-94 HB).

Properties	AEROBOND™
Appearance	Yellow Viscous Liquid
Solid Content	19.5 ± 0.5%
Specific Gravity at 25°C	0.86-0.88
Viscosity at 30°C	3000-3500 cps
Open Time	30-90 minutes
Coverage Area	7-10 m ² /litre

*Net Weight.16 kgs. **Coverage area. 60 m²/bucket

แอโรบอนด์

คือ กาวยางโพลีคลอโรพรีนสูตรพิเศษ เพื่อให้เหมาะกับการใช้ในการประสานฉนวนโฟมยาง (เช่น แอโรฟлекс และแอโรเซล) และฉนวนใยแก้วที่ติดกับแผ่นโลหะของท่อส่งลม สามารถยึดประสานฉนวนกับแผ่นโลหะได้เป็นอย่างดี ด้วยแรงยึดเกาะสูงถึง 4 กิโลกรัมต่อตารางเมตร แม้จะใช้ในอุณหภูมิถึง 93°C

วิธีใช้

1. พื้นผิวของแผ่นโลหะ และแผ่นฉนวนต้องสะอาด ปราศจากน้ำ น้ำมัน ฟัน หรือสิ่งสกปรกต่าง ๆ
2. ทากาว แอโรบอนด์ ให้สม่ำเสมอทั่วพื้นที่แผ่นโลหะ รอให้กาวแห้งเล็กน้อย จากนั้นนำแผ่นฉนวนมาประกบ บนแผ่นโลหะ โดยปกติจะมีเวลาให้ประกบภายในระยะเวลา 30 นาที กดแผ่นฉนวนให้แน่นเต็มพื้นที่ที่ทากาว

การเก็บรักษา

กาว แอโรบอนด์ สามารถเก็บไว้ได้นานกว่า 8 เดือน ในภาชนะที่ปิดสนิท ดังนั้นหลังการใช้กาวทุกครั้ง ควรปิดฝาให้สนิท และเก็บไว้ในที่ร่มที่อุณหภูมิ 5°C-35°C และไม่ถูกแสงแดดโดยตรง

ข้อควรระวัง

กาว แอโรบอนด์ มีส่วนผสมของสารตัวทำละลาย ที่ระเหยเร็วและ มีความไวไฟ จึงควรใช้กาวในบริเวณที่มีการระบายอากาศได้ดี ควรวางห่างจากแหล่งความร้อน ประกายไฟ เปลวไฟ และวัสดุที่ติดไฟได้ง่าย เช่น กระดาษ ขี้ยา พลาสติก ฯลฯ กาว แอโรบอนด์ เมื่อแห้งแล้ว จะเป็นวัสดุชนิดติดไฟได้เอง ตามมาตรฐาน UL-94 HB.

*น้ำหนักสุทธิ 16 กก. ***1 ถังทากาวได้ 60 ตร.ม



บริษัท 3ที อินซูลेशन จำกัด

ที่อยู่ 20/8 หมู่ 10 ถ.กาญจนภิเษก ต.คลองข่อย อ.ปากเกร็ด จ.นนทบุรี 11120

โทรศัพท์ 02-159-6402 , 02-159-0601-2

Email sales@3t-insulation.com

Website www.3t-insulation.com

