

ProRox® BL 960^{SA}

ProRox BL 960^{SA} is a blanket type product used in thermal insulation of non-vibrating industrial equipment's where temperatures can be up to 650 deg Celcius.



Product properties

Properties	Performance							Standard
Thermal conductivity	T _m (°C)	50	100	150	200	250	300	ASTM C177
	λ (W/mK)	0.041	0.049	0.057	0.066	0.074	0.083	
Norminal density	100 kg/m ³							ASTM C167
Maximum service temperature	650 °C							ASTM C411/C447
Linear shrinkage	Less than 2% (at max service temperature)							ASTM C356
Reaction to fire	EuroClass A1 Surface burning characteristics; Flame spread = passed, Smoke development = passed							EN 13501-1 ASTM E84
Chloride content	Less than 10 ppm Conforms to the stainless steel corrosion specification as per ASTM C795							ASTM C871 ASTM C692/C871
Moisture absorption	Less than 1% weight							ASTM C1104/ C1104M
Water absorption	Less than 1 kg/m ²							EN 1609

Note: All information and data for technical parameters are based on laboratory testing.

Compliance

- ProRox BL 960^{SA} Blanket fully comply with the requirements as set by internationally recognized standards like ASTM C553 Type I, II, III, IV, V, VI and VII.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL (Thailand) Limited

B.Grimm Building 11th Floor, 88 Krungthepkreetha Road, Huamark Bangkokkapi, Bangkok 10240, Thailand
T (+66) 2731 7511
F (+66) 2731 7510

Vietnam Representative Office

ROCKWOOL (Thailand) Limited
9th Floor, TNR Tower
180-192 Nguyen Cong Tru Street
District 1, Ho Chi Minh City, Vietnam
T (+84) 8 6288 2009
F (+84) 8 6288 4691